

SVE Wood Finish PU Topcoat Paint

PRODUCT DESCRIPTION: SVE Wood Finish PU Topcoat finish is a quality product, which is formulated specially for the protection of your wood, and helps preserving the shininess of the wood for longer years.

It provides a glossy durable film which helps protecting your wood from water, alcohol and usual household chemicals, thus giving attractive finish to the surface of protection. . It is designed to keep your interior & exterior surfaces beautiful for long with non –yellowing property compared to traditional synthetic based enamel.

It has long retention and has excellent adhesion with long life.

For Variety refer to Shade Card

TECHNICAL DETAILS:

Coverage: 1st Coat 180 to 200 Square Feet /Ltr

2nd Coat 90 to 100 square Feet/Ltr

Drying time: 6 to 8 Hrs

Specific Gravity: 1.16

Viscosity: 120 sec by B4 Ford cup

Shelf Life: 24 months

PERFORMANCE FEATURES & BENEFITS:

- Rich gloss PU Based enamel.
- Anti-fungal property.
- Non –yellowing resin system.
- Interior & exterior durable
- Superior Hiding & Coverage
- Wash ability – High
- Recommended surface – Wood after appropriate priming.

APPLICATION DETAILS & SURFACE PREPERATION:

- Shake well before use
- Using tools: Brush/Roller/Spray
- Thinner : SV E PU Thinner(T-10)
- Surface Drying : 60 Minutes
- Filling – SVE Putty

- Wipe the surface clean to make it free from dust, dirt, grease etc.
- Dents & imperfections can be filled using SVE Filler/ Putty, which shall be sanded and primed again.

Directions of use:

- **Mixing Ratio:** PU paint & hardener in the ratio of 8:2 & allows it to mature for 30 minutes.
- This mixture is mixed with 40 % SVE T10 thinner.
- After coating leave it for 10 to 12hours.

1st Coat PU Paint: Sand the surface again the orbit sander machine with disc of grit 400 and clean the surface with a soft cloth. Apply the first coat of PU Paint with spray gun and leave it for the next 12 hours to dry.

Wet sanding: After first coat of PU Paint, do the wet sanding of the surface with emery paper of grit 1000. This wet sanding removes the excess material and creates a smooth base for the final coat.

Final coat: After wet sanding apply the second coat of PU Paint with spray gun and leave it for 12 hours to dry.

Buffing: Buffing is optional, but we at Home Glazer advice buffing for Gloss finish. For Matt finish, buffing is not advisable

APPLICATION ENVIRONMENT:

Temperature: 10 to 40°C

Humidity: Below 70°C

PRECAUTION:

Do not over thin

Pack Available: 1litre, 4litre, 20litre